



Product Usage Chart

S. No.	Product	Properties	Benefits	Usability/Area of application
1.00	ENIROOF GOLD (Acrylic polymer modified, high solid, flexible, durable Liquid Membrane coating)	Gray Paste, 700-800 % Elongation, 95-97% Set tensile recovery, Tear resistance 28 KN/M, Heat resistance 120° C, Bond Strength 3.3 KN/SM, Flammability and toxicity 0.95± 0.1, UV Stable, Temp. range -25 to 120°C, Crack bridging 1.5 mm	Easy to apply, Water based, Eco friendly, better bonding to surface, can be applied on any shape, compatibility with almost all building materials	Waterproofing of terrace, Terrace garden, Deck slab, retaining wall
2.00	ENIROOF EMB® (polymer modified flexible Liquid Membrane coating)	Brownish Black thixotropic liquid , 900-1000 % Elongation, 95% Set tensile recovery, Tear resistance 28 KN/M, Heat resistance 120° C, Bond Strength 3.3 KN/SM, Flammability and toxicity 0.95± 0.1, Temp range -25 to 120°C	Easy to apply, Water based, Eco friendly, better bonding to surface, can be applied on any shape, compatibility with almost all building materials	Waterproofing of terrace, Terrace garden, Deck slab, retaining wall

3.00	ENIROOF SPR® (Acrylic polymer modified white Liquid Membrane coating)	White Paste, 200-250 % Elongation, 98%-100% Set tensile recovery, Tear resistance 4 KN/M, Heat resistance 120° C, Bond Strength 60 Psi, Flammability and toxicity Non Flammable non toxic, UV Stable, Temp range -25 to 120°C	Easy to apply, Water based, Eco friendly, better bonding to surface, can be applied on any shape, compatibility with almost all building materials	Waterproofing of open terrace, old structure roof, Skylight, Polycarbonate sheets, AC Sheet, MS sheet, Vertical walls
4.00	ENITHANE BLK (Polyurethane based, high solid Moisture cure, single component liquid membrane coating)	Black high solid liquid, Shore OO 65, Tensile strength 1 Mpa, Elongation 500-600%, Crack bridging capacity 1.5 mm, water vapor permeability 0.1	Easy to install, very good water resistance. UV stable, Resistance to mild acid and ozone	Deck slab waterproofing, terrace and terrace garden waterproofing, as pond liner
5.00	STAR SEAL 100 (EPDM Rubber Sheet)	Black continuous rubber sheet. Shore A 65±5, Tensile Strength 100 Kg/ CM ² , Elongation at break 350%, Tear resistance 35 kg/cm, polymer content 50% (neoprene). Temp range -50 to 150°C	Easy to install, very good water resistance. UV stable, Resistance to mild acid and ozone	Deck slab waterproofing, terrace and terrace garden waterproofing, as pond liner
6.00	Di Primer (SBR Polymer based Universal primer for coatings application)	Milky white low viscous liquid. Very fine particles	seals the surface and pores, increase bond ability of coatings	As primer coat for liquid membrane applications, as additive in general concrete repairs

7.00	AQUAGUARD 50%® (Acrylic polymer based Coating)	White thick liquid, Active polymer content 48±2, Flexible, UV stable	Easy application, Weather proof, excellent compatibility with cement, excellent bond strength	For making cement slurry for waterproof coating application. Down slab waterproofing. As bonding agent
8.00	AQUACRETE 30%® (SBR polymer based Coating)	White thick liquid, Active polymer content 28±2, Flexible, High water resistance	Easy application, excellent compatibility with cement, excellent bond strength	For making cement slurry for waterproof coating application. Down slab waterproofing. As bonding agent, making slurry for grouting. Concrete repair
9.00	ENIROOF CLEAR (Urethane based clear waterproof and anticorrosion coating for concrete metal and wood structures)	Clear Thick liquid, quick drying, weather resistance, UV stable	Easy to apply with brush roller and spray, very good water resistance. UV stable, Resistance to mild acid and alkali	Waterproof protective coating for metal, stone, wood and concrete structure
10.00	Admixture and Plasticizers	Available in different bases (Lingo sulphonate/ SNF/PC/ PC 3rd generation)	Improve workability, strength, reduce porosity, reduce cement water ration	produce high early strength concrete, compact concrete

Technical Support:



& Polymertech UK Ltd.
CN-07468396
United Kingdom